

TSA Directional Discrete TGSI Poly - 20mm Single Stem

20 Feb 2017

Client Details & Test Information :

This Report Is In Accordance with	AS 4586 (New)
Testing carried out using the Wet Test Method and	Slider 55 (TRL) Rubber slider
Date Tested:	20 Feb 2017
Test Report Number:	KO200217-5
Client Name / Billing Address:	Tactile Systems Australia - 6/168 Siganto Drive Helensvale Q4212
Property Tested:	TSA Directional Discrete TGSI Poly - 20mm Single Stem

Pre-Start Checklist :

Record ambient temperature (°C)	30
Temperature Correction for Type 55 (TRL) Rubber Slider	27-33 = +2
Record weather	Indoors
Record Weight & Batch/Expiry of Sliders : Check Contact surface Under 4mm	Slider 55 (TRL) 35g / #92

RESULTS :

Mean BPN Slip Resistance Value (SRV)	21
Corrected Mean BPN (SRV) Slider 55 ONLY	36
Variation of Standards	VARIATION OF STANDARDS - ONLY 1 SAMPLE AVAILABLE FOR TESTING
Under 4586:2013 The Australian Standards Recommend for this area	N/A - No Information Provided
Using Slider 55 (TRL) you have achieved a BPN of	P3 = 35 - 39 : "In-Line with R10/A ref SA HB 198:2014"
Do my Results meet the Australian Standards ?	N/A - No Information Provided

*** Note regarding 'R' RATINGS : Please note there is NO direct correlation between a R Rating and a P Rating (Wet Pendulum Test. Please refer to SA HB198:2014 for further information.**

Testing Officer Signature & Comments :

Testing Officer :	Kathryn Ording
Pendulum machine in use - Caibration Date :	Munro Portable Skid Tester # 1133 - 24.08.2015
Testing Officer Signature	

TEST INFORMATION & PICTURES :

Test Location & Pictures

Location	Grade Degrees	Swing 1	Swing 2	Swing 3	Swing 4	Swing 5	Mean BPN Test	Slope Correction Value (SCV)	Photo of Test Site
Area 1	< 1.5	40	36	35	35	35	35	N/A	
Area 2	< 1.5	34	30	30	30	30	30	N/A	
Area 3	< 1.5	39	38	38	38	38	38	N/A	

Declaration:

The factual matters stated within this report are, to the best of my knowledge, true and correct. I have completed all enquiries that I consider appropriate in formulating my conclusions. The opinions stated by me within this report are genuinely held by me. The report contains reference to all matter which I regard as significant. I understand that my overriding duty as an expert is to assist the Court and have complied with this duty.

This report and covering documentation was prepared by Sliptest Australia Pty. Ltd. on behalf of our client as named in the report. Neither Sliptest Australia Pty. Ltd. nor any person acting on our behalf (a) makes any warranty, express or implied, with respect to the use of any information or methods disclosed in this report or (b) assumes any liability with respect to the use of any information or methods disclosed in this report or covering information. Any recipient of this document, by their acceptance or use of this document, releases Sliptest Australia Pty. Ltd. and their affiliates from any liability for direct, indirect, consequential or special loss or damage whether arising in contract, warranty, express or implied, tort or otherwise, and irrespective of fault, negligence and strict liability.?

The information presented herein and on the Sliptest Report is copyright and is protected by copyright law, any reproduction of this information and test report except in full is prohibited. Any enquiries in relation to this report should be directed to Sliptest Australia Pty. Ltd. quoting the applicable test report number. Sliptest Australia Pty. Ltd. performed this on site test with reference to the following Australian Standard testing criteria, of AS 4586:2013 Classification of new pedestrian surface materials. Appendix A – Wet Pendulum Test Method and Hand Book HB 198: 2014 with reference to AS/NZS 4663: 2004 Slip Resistance measurement of existing pedestrian surfaces and HB 197: 1999